

Radamex Brzozowa 1; 05-822 Milanówek; rzepy@rzepy.net; www.rzepy.net

Sew-On Hook & Loop Grade 101


Issue Date: 13th August 2020


Version:1

Issued by: K. Astley

Technical Information:

Sew-On/Hook	Sew-On/Loop
Base Material: Polyamide 100%	Base Material: Polyamide 100%
Construction: Standard with woven with cold -cut sewing edges.	Construction: Standard with woven with cold -cut sewing edges.
Width Tolerance: +/- 5%	Width Tolerance: +/- 5%
Weight: 315g/m ² (+/-10%)	Weight: 335g/m ² (+/-10%)
Thickness: 2 mm (+/- 0.5mm)	Thickness: 2,2 mm (+/- 0.5mm)
Standard Width Available: 16mm, 20mm,25mm,30mm, 38mm,50mm,100mm, 150mm	Standard Width Available: 16mm, 20mm,25mm,30mm, 38mm,50mm,100mm, 150mm
Standard Length: 25 metres	Standard Length: 25 metres

Peel Strength ASTM D5170 / EN 12242	Average:
	
After 1 opening & closing cycle	1.75 N/cm
After 5000 opening & closing cycle	1 N/cm
After 10000 opening & closing cycle	0.7 N/cm

Shear Strength ASTM D5169 / EN 13780	Average:
	
After 1 opening & closing cycle	9.75 N/cm ²
After 5000 opening & closing cycle	3.5 N/cm ²
After 10000 opening & closing cycle	3 N/cm ²